



PD P2AO 350 Oil / Permawick  
 REV. # 3  
 REV. DATE: Oct 9<sup>th</sup>, 2007

255 E. Brown Street. Ste. 100, Birmingham, MI, 48009  
 Phone: 248-433-3500 • Fax: 248-433-1824  
 Email: [sales@permawick.com](mailto:sales@permawick.com)  
<http://www.permawick.com>

## P2AO350 Oil and PERMAWICK

### PAO based synthetic lubricant for Sintered Metal Bearings

#### DESCRIPTION

PERMAWICK P2AO350 OIL is especially developed for plastic compatibility for use in the fractional horsepower electric motor industry. This lubricant possesses extremely long service life and resists any leakage or washing away that could cause dry running. Low pour point and high viscosity index provide superior low temperature fluidity.

PERMAWICK P2AO350 OIL is hydrolytically stable oil with remarkable thermal and chemical stability and has a wide use range of -40 to 125°C.

#### PRODUCT FEATURES

- Oxidation and corrosion resistant
- Reduced rate of change of viscosity with temperature change
- Separates easily from water
- Mixes with conventional mineral oils
- Reduces friction and wear
- Will not lose lubricating characteristics when contaminated

<u>PERFORMANCE TEST (Oil)</u>	<u>ASTM METHOD</u>	<u>TYPICALS</u>
ISO VG	D2422	68
Gravity, API	D1298	37.56
Specific Gravity	D1298	0.8373
Color	D1500	<1.0
Flash Point, °C	D92	232
Fire Point, °C	D92	270
Pour Point, °F	D97	-57
Viscosity, cSt	D445	
40 °C		67.88
100 °C		10.59
Viscosity Index	D2270	144
Viscosity, SUS	D88	
100 °F		351
210 °F		56
Neutralization No., mg KOH/g	D664	0.01
Copper Strip Corrosion	D130	
3 hours @ 100°C		1B (min)
Evaporation Loss, wt. %	D972	
22 hours @ 100 °C		0.1
<b><u>PERMAWICK BLEND</u></b>		
Fiber content	In-house	14% - 19%
Oil Content	In-house	86% - 81%
Moisture Content	D95	<1.6%

**The World Leader in Fractional Horsepower Motor Lubrication**

**Permawick Product Data Sheet**